

MOLYKOTE® P-3700 Anti-Seize Paste

High-purity solid lubricant paste for bolted joints used in high-temperature environments including steam & gas turbines, turbochargers

Features

- Provides controlled friction during assembly to support exact tensioning
- Excellent anti-seize properties: Allows screws to be removed easily, even after long-term exposure at high temperatures
- Applicable for chromium-containing alloys, even at elevated temperatures
- Free of intentional calcium ingredients
- High-purity paste (impurity sulfur, calcium and total halogen content regularly monitored)
- Environmentally friendly and health-friendly – no hazard labeling and precautionary statements


Responding to market needs and the trend towards more sustainable products

Threaded connections in high-temperature-operating applications such as turbines and turbochargers require health-friendly lubrication to avoid seizing and to provide proper tightening torque. MOLYKOTE® P-3700 Anti-Seize Paste provides these features over a wide service-temperature range of -30°C to 900°C, enabling maintenance after long periods of time at elevated temperatures to minimize material usage and waste. In addition, MOLYKOTE® P-3700 Anti-Seize Paste is equipped with a friendly EHS profile while still providing high performance under stress.

Screw test results

Constant forces over multiple tightenings

Testing in the Schatz screw tester shows that MOLYKOTE® P-3700 Anti-Seize Paste provides repeatable constant forces over multiple tightenings (5), independent of screw type.



Suppression of hexavalent chromium formation

MOLYKOTE® P-3700 Anti-Seize Paste successfully suppresses formation of yellowish hexavalent chromium Cr(VI) at high temperatures while still offering fully functional anti-seizing property.



Lubricated stainless steel bolts after exposure to >500°C





Typical properties of MOLYKOTE® P-3700 Anti-Seize Paste

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Result
	Appearance	Dark gray
Consistency, density		
ISO 2137	Unworked penetration	280 to 320 mm/10
ISO 2811	Density at 20°C	1.23 g/cm ³
Temperature		
	Service temperature range ⁽²⁾	-30 to +900°C
Loading capacity, protection against wear, service life		
DIN 51350 T.4	4-ball weld load	3,000 N
DIN 51350 T.5	4-ball wear scar under 400 N load	1.1 mm
Coefficient of friction & threaded connections		
Screw test: Schatz tester	M12 x 1.75 mm, 8.8, blackened surface	
	μ thread (avg.)	0.10
	μ head (avg.)	0.10
	K-factor (avg.)	0.14
Screw test: Schatz tester	M12 x 1.75 mm, A2-70, 1.4301, blank	
	μ thread (avg.)	0.11
	μ head (avg.)	0.09
	K-factor (avg.)	0.14
Internal	Initial breakaway torque after 540°C/21 hr on 1.7709, M12, blackened (start torque = 56 Nm)	~120 Nm

⁽¹⁾ISO: International Standardization Organization. DIN: Deutsche Industrie Norm. | ⁽²⁾Temperature resistance of solid lubricants.

About MOLYKOTE® Specialty Lubricants

For more than 70 years, customers around the world have trusted the MOLYKOTE® brand for performance and expertise to solve or prevent virtually any lubrication problem and to save energy. Available through a global network of more than 3,000 channel partners, MOLYKOTE® brand lubricants – which include well over 500 anti-friction coatings, compounds, dispersions, greases, oils and fluids, and pastes – serve the automotive market and industrial/maintenance, repair and overhaul (MRO) markets. To learn more about our extensive product and service offering or to locate a distributor, visit molykote.com.



Contact us

MOLYKOTE® has Contact Centers around the globe. Find the phone number for the center nearest you at www.dupont.com/molykotecontact.



DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2022 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.